

U.S. EROSION CONTROL PRODUCTS, INC. (ERO-GUARD WEST)

Material and Specification Sheet EG-2P10 Turf Reinforcement Mat (TRM)

Description: EG-2P10 starts with 100% green polypropylene fiber that is distributed evenly between 2 black heavy weight UV stabilized nets. These nets are then stitched using black UV stabilized creating one of the highest quality blankets available on the market. The rolls are then tightly shrink wrapped and packaged to handle adverse conditions until they are installed.

EG-2P10 has been engineered as a turf reinforcement mat (TRM). Its functional longevity is greater than 36 months (which depends on environmental conditions such as light, wind, water and soil conditions).

Composition:

Matrix	Netting	Thread
100% Polypropylene Fiber	Heavy UV Stabilized	Heavy UV Stabilized
.625 lbs/SqYd	.75" x .75" Opening	1.5 inch traverse stitching

UNVEGETATED DESIGN VALUES	Value	Index Values		
		Test Property	Test Method	Value
Max Permissible Shear Stress	2.5 lb/ft ²	Mass/Unit Area	ASTM 6475	10.0 oz/yd ²
Max permissible Velocity	7.1 ft/sec	Thickness	ASTM 6525	9.2 mm
Shear relation (.06 lb/ft ²) Tau lower	n = 0.035	Tensile Strength-MD	ASTM 6818	21.2 lbs/in
Shear relation (1.2 lb/ft ²) Tau middle	n = 0.029	Elongation-MD	ASTM 6818	30.5 %
Shear relation (.06 lb/ft ²) Tau upper	n = 0.029	Tensile Strength-TD	ASTM 6818	18.0 lbs/in
		Elongation- TD	ASTM 6818	20.2%
		Light Penetration	ASTM 6567	26%

Vegetated Design Values	Value
Max Permissible Shear Stress	12.0 lb/ft ²
Max Permissible Velocity	15.0 ft/sec

*Index values are average values at the time of manufacture and are characteristic of the product. For more information, please contact your nearest Ero-Guard distributor.

Your Leader In Erosion Control Blankets

26368 I-76 Frontage Road · Keenesburg, CO · 80643-9444
Phone: (888) 922-0840 · Fax: (303) 990-5261



Made in the U.S.A.